

## Description

Soft PVC film which conforms well to the substrate. Available in more than 50 colours with a matt surface.

## Release Paper

Silicone coated paper on one side, 135 g/m<sup>2</sup>. For white vinyl, a light blue silicone paper is used, to form a stronger contrast to lettering.

## Adhesive

Polyacrylate, removable

## Area of use

For indoor applications such as markings, inscriptions and decorations, especially on inner walls. Very well suited for use on cutting plotter systems. It is recommended to use the application tape ORATAPE® LT 95.

## Certificates

Fire behaviour (DIN EN 13501-1): B-s2, d0 (flame resistant, limited smoke production, no flaming droplets/particles). Only valid for application to substrates made from gypsum boards or other substrates which are classified as A1 or A2-s1, d0 with a thickness of ≥ 6 mm and a density of ≥ 450 kg/m<sup>3</sup>.

## Technical Data

<b>Thickness*</b> (without protective paper and adhesive)	80 micron
<b>Dimensional stability</b> (FINAT TM 14)	Adhered to steel, no measurable shrinkage in cross direction, in length 0.4 mm max.
<b>Temperature resistance***</b>	Adhered to aluminium, -40° C to +80° C, no variation
<b>Adhesive power*</b> (FINAT TM 1, after 24h, stainless steel)	6 N/25 mm
<b>Tensile strength</b> (DIN EN ISO 527)	Along: min. 19 MPa Across: min. 19 MPa
<b>Elongation at break</b> (DIN EN ISO 527)	Along: min. 130% Across: min. 150%
<b>Shelf life**</b>	2 years
<b>Application temperature</b>	> +10° C
<b>Service life by specialist application</b> (Indoor use)	2 years
<b>Removability</b>	Removable from most surfaces without residue

\* average \*\* in original packaging, at 20° C and 50% relative humidity

## Note

Surfaces to which the material will be applied must be thoroughly cleaned and free from dust, grease or any other contamination that could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. Furthermore, the application information published by ORAFOL must be considered. The batch traceability according to ISO 9001 is possible on the basis of the roll number.

### **IMPORTANT NOTICE**

All ORACAL® products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning ORACAL® products is based upon research which the Company believes to be reliable although such information does not constitute a warranty. Because of the variety of uses of ORACAL® products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. All specifications are subject to change without prior notice.

ORACAL® is a registered trademark of ORAFOL Europe GmbH.